

Appn: No. 09/606,878
Amendment dated September 5, 2003
Reply to Office Action of June 6, 2003

This listing of claims will replace all prior versions, and listing, of claims in the application.

LISTING OF CLAIMS:

1. (Currently Amended) A method of treating a surface of a substrate containing titanium for an ornament, the surface of the substrate having been subjected to a machine working by any of a honing processing step, a nicking processing step and a mirror finishing step and as a result having a substance adhered thereto, the substance being a foreign material, comprising the steps of:

providing the surface containing titanium;

eliminating the substance adhered to said surface of said substrate from said surface; and

forming a transparent protective layer containing glass by the steps of;

selecting a glass coating liquid containing water and having a viscosity that is between 200-500 cps at 25°C when the substrate has been subjected to the honing processing step or the nicking processing step, and that is between 150-250 cps at 25°C when the substrate has been subjected to the mirror finishing step,

applying the glass coating liquid chosen in the selecting step on said surface from which said adhered ~~substances have~~substance has been removed~~eliminated~~, and

drying said surface.

2-4. (Cancelled).

Appl. No. 09/606,878
Amendment dated September 5, 2003
Reply to Office Action of June 6, 2003

5. (Currently Amended) The method of claim [[4]]1, wherein said glass coating liquid is dried for about 1 to 20 minutes at a temperature in the range of about 20°C to 250°C.

6. (Currently Amended) The method of claim [[4]]1, ~~including the steps of forming~~ wherein said glass coating liquid is formed by the steps of:
providing an original liquid and a diluting solvent; and
by diluting an the original liquid with a the diluting solvent.

7. (Currently Amended) The method of claim 1, wherein the step of ~~removing substances~~ eliminating the substance adhered to said surface of said substrate includes chemical polishing said surface by immersing said surface in an etching solution.

8. (Original) The method of claim 7, wherein said etching solution comprises hydrofluoric acid, nitric acid and sulfuric acid.

9. (Original) The method of claim 8, wherein said etching solution is an aqueous solution comprising 1% to 10% volume of hydrofluoric acid, 15% to 40% volume of nitric acid and 30% to 60% volume of sulfuric acid.

10. (Original) The method of claim 7, wherein the temperature of said etching solution is in the range of about 30°C to 75°C.

11. (Original) The method of claim 7, wherein said surface is immersed in said etching solution for about 5 to 50 seconds.

Appln. No. 09/606,878
Amendment dated September 5, 2003
Reply to Office Action of June 6, 2003

12. (Currently Amended) The method of claim 1, wherein the step of eliminating said adhered ~~substance~~substance includes electropolishing said surface with an electrolyte solution.

13. (Original) The method of claim 12, wherein said electrolyte solution contains phosphoric acid.

14. (Original) The method of claim 12, wherein said electropolishing procedure employs an anodic current density in the electrolyte solution of about 0.5 to 10 Amps/cm².

15. (Original) The method of claim 12, wherein said electropolishing step is performed for about 3 seconds to 2 minutes.

16. (Currently Amended) The method of claim 12, wherein the electrolyte solution contains H₃PO₄ in a concentration in the range of about 8% to 12 % volume.

17. (Currently Amended) The method of claim 1, wherein said step of eliminating said adhered ~~substance~~substance includes washing said surface.

18. (Currently Amended) The method of claim 1, wherein said ~~substance~~substance adhered to said surface of said substrate contain titanium oxides that cause blackening of the surface.

19. (Cancelled).

Appl. No. 09/606,878
Amendment dated September 5, 2003
Reply to Office Action of June 6, 2003

20. (Currently Amended) The method of claim 6, wherein the step of forming said glass coating liquid includes selecting a dilution ratio corresponding to a selected said machine work and diluting said original liquid to a dilution ratio corresponding to said selected machine work applied to said surface.

21. (Currently Amended) The method of claim 20, wherein said glass coating liquid has a viscosity of 150 cps ~~(25°C)~~ at 25°C or greater and a dilution ratio in the range of about 30% to 70%.

22. (Currently Amended) The method of claim 20, wherein said glass coating liquid has a viscosity in the range of about 150 to 400 cps ~~(25°C)~~ at 25°C and a dilution ratio in the range of about 50% to 98%.

23. (Currently Amended) The method of claim ~~[[4]]~~, wherein the step of drying said surface includes drying said surface at least two times under different drying conditions.

24. (Currently Amended) The method of claim 12, wherein ~~the~~ a pH of the electrolyte solution is in the range of about 1.0 to 1.2.

25-39. (Cancelled).

40. (Currently Amended) The method of claim 1, wherein said ornament is a part of a timepiece.

41-42. (Cancelled).

Appln. No. 09/606,878
Amendment dated September 5, 2003
Reply to Office Action of June 6, 2003

43. (New) A timepiece containing an ornament made by the method of treating a surface as in claim 1.